

NON-SAG TEXTURED SEALANT

Multi-Purpose Hybrid Silane Polyether



PRODUCT DATASHEET

DESCRIPTION: Rapid Set® NON-SAG TEXTURED SEALANT is a single-component, multipurpose, fast curing, non-sag, UV stable sealant. This high-performance sealant incorporates texturizing aggregate designed to complement most texturized surfaces. Its hybrid silane polyether chemistry enhances both adhesive and cohesive bond, prevents shrinkage upon cure, provides high tensile strength and flexibility, exceptional durability, and weather resistance. NON-SAG TEXTURED SEALANT promotes superior adhesion that outperforms the bond strength of polyurethanes, and will not foam on damp surfaces. This environmentally friendly formulation has a low VOC content, is 100% solvent free, and contains no isocyanates.

USES: Use NON-SAG TEXTURED SEALANT for interior and exterior applications. Its superior sag resistance makes it ideal for use on horizontal, vertical and overhead applications, including: filling wall joints, control joints, expansion joints, cove joints, and cracks; sealing windows, and door frames. It is engineered for use on exterior balconies, concrete floor slabs, driveways, garages, patios, walkways, and other vertical, horizontal, and overhead applications. This material provides excellent adhesion to PVDF coated metal, galvanized metal, aluminum, wood, glass, cement board, brick, concrete, stone, aged asphalt, EPDM and SBS-modified bitumen membranes, EPS foam, roofing materials, fiberglass (FRP), vinyl siding, and masonry. It can be used in damp, dry or cold climates, and its excellent adhesion characteristics make it ideal for application to damp concrete substrates.

ENVIRONMENTAL ADVANTAGES: Low VOC, 100% solids, isocyanate-free products are ideal for applications where the presence of VOCs, fumes or vapors are unacceptable, undesirable or impractical. These products reduce the health risks of building occupants, installers and contractors; and contribute to improved indoor and outdoor air quality. Maximum durability and service life minimizes construction waste byproducts.

REGULATORY COMPLIANCE: Conforms to OTC rule for sealants. Meets requirements of California Regulations: CARB, BAAQMD and SCAQMD. Conforms to USDA requirements for non-food contact.

GREEN STANDARDS: LEED 2.2 for new construction and major renovations: Low emitting materials (section 4.1) 1 Point. National Association of Home Builders (NAHB) Model Green Home Building Guidelines: 5 global impact points. VOC Content: 12.45 grams / liter per ASTM D2369. EPA Method 24 (tested at 240°F/ 115°C).

SURFACE PREPARATION: Ensure substrate is clean, sound, and free of bond inhibitors, such as grease, oil, mold, surface water, coatings and sealers. For best results, roughen surfaces with an abrasive disc or sand paper, then wipe with acetone. Tape off or protect adjacent areas.

APPLICATION: Apply between a minimum temperature of 35°F (2°C) and rising, and a maximum of 100°F (38°C). For best results, place sealants between 70°F (21°C) and 80°F (27°C). Typical width to depth ratio is 2:1. Cut the end of the nozzle to match the width of the joint and insert a tool to puncture the inner foil seal. Ensure the opening size of the nozzle and foil seal are large enough to allow proper flow. Too small an opening could result in excessive back pressure leading to failure of the rear seal. Insert the cartridge into a caulking gun. Before placing, extrude material until an even color (without streaks) flows out of the nozzle. Place nozzle at bottom of joint or application area to avoid trapping air during placement. Keep the nozzle in the material during application. Using constant pressure, carefully apply the sealant with a smooth continuous bead. If tooling is needed, do so within 15 minutes of application.

OVERVIEW

Highlights:

Complements roughly textured surfaces

Fast Curing: 15-minute working time, tack-free in 35 minutes, paintable in 1 hour

Strong Bond: Excellent adhesion to dry and damp substrates

Interior/Exterior: Durable in tough environments

Horizontal, vertical and overhead use

Superior sag resistance

Weather and UV resistant. Non-shrink

100% solids, low VOC, no odor, and no harmful isocyanates

Conforms to:

ASTM C920, Type S, Grade NS, Class 35, uses NT, T2, M, G, A, & O

Federal Specification TT-S-00230-C, Type II, Class B

Army Corps of Engineers CRD-C-541, Type II, Class B

Canadian Standards Board CAN 19,13-M-82

MasterFormat® 2016

07 01 90 Joint Sealant Rehabilitation/Replacement

07 92 13 Elastomeric Joint Sealants

Manufacturer:

CTS Cement Manufacturing Corp.
12442 Knott St.
Garden Grove, CA 92841
Tel: 800-929-3030 | Fax: 714-379-8270
Web: www.CTScement.com
E-mail: info@CTScement.com



NON-SAG TEXTURED SEALANT Multi-Purpose Hybrid Silane Polyether

CRACK/JOINT FILLING: Place backer rod, where required, to prevent three-sided bonding. Concrete joints (tooled or saw cut) must be free of contaminants and the concrete must have at least 72 hours of cure before placement.

CLEAN-UP: Remove excess material, using acetone and disposable paper towels or cloth rags, before it cures on placement tools and adjacent surfaces. Dispose of waste material in compliance with local regulations.

CURING: Tack-free in 40 minutes; paintable in 1 hour at 1/4" at 70°F (21°C), 50% relative humidity.

COLD WEATHER: Installation in low temperatures will extend cure times of the Rapid Set® NON-SAG TEXTURED SEALANT. To ease flow and placement in cold conditions, warm and keep the sealant at 70°F (21°C) 24 hours prior to installation. Remove dew, frost or ice from the substrate with acetone on a clean cloth and place sealant immediately.

WARM WEATHER: Installation in warmer temperatures 80°F to 100°F (27°C to 38°C) will not adversely affect sealant performance. Warmer temperatures will decrease viscosity and shorten cure time.

PACKAGING: Available in single-component, 10.1 fl. oz. (299 mL) cartridge.

COLORS: Gray.

COVERAGE: 10.1 fl. oz. (299 mL) yields 18.2 in³, 96 linear feet for 1/8" x 1/8" joints, 48 feet for 1/8" x 1/4" joints, 24 linear feet for 1/4" x 1/4" joints, 12 linear feet for 1/4" x 1/2" joints.

10.1 FLUID OUNCE (299 ML) COVERAGE RATE

Depth of Joint, Inches	Width of Joint, Inches	Linear Feet Per Cartridge
1/8	1/8	96
1/8	1/4	48
1/4	1/4	24
1/4	1/2	12

SHELF LIFE: NON-SAG TEXTURED SEALANT has a shelf life of 18 months from the date of manufacture when properly stored.

STORAGE: Store in original, unopened container in a cool, dry area. Protect unopened container from water, heat and direct sunlight. Store at 40°F to 90°F (4°C to 32°C). Elevated temperatures will reduce shelf life.

LIMITATIONS: Do not apply greater than 1" width and 1/2" depth. Do not use in continuous immersion applications. Allow treated wood and asphalt to cure for six (6) months prior to application of NON-SAG TEXTURED SEALANT. Do not apply on frozen substrates. Test and evaluate all paints and coatings before applying to NON-SAG TEXTURED SEALANT. Polyurethane and oil based paints may dry slowly.

USER RESPONSIBILITY: Before using, read current technical data sheets, bulletins, product labels and safety data sheets. It is the user's responsibility to review the instructions and warnings for any CTS products prior to use.

Refer to the Safety Data Sheet and www.CTScement.com for additional safety information regarding this material.

WARNING: AVOID CONTACT WITH SKIN AND EYES. Can cause skin irritation, may cause an allergic skin reaction, causes serious eye irritation. Wear protective gloves/protective clothing/eye protection. In case of contact with eyes rinse immediately with plenty of water and seek medical advice.

LIMITED WARRANTY: CTS Cement Manufacturing Corp. (CTS) warrants its materials to be of good quality and at its option, within 18 months from date of manufacture, will replace material proven defective or refund purchase price thereof, and such replacement or refund shall be the limit of CTS's responsibility. Except for the foregoing, all warranties, expressed or implied, including merchantability and fitness for a particular purpose, are excluded. CTS shall not be liable for any consequential, incidental, or special damages arising directly or indirectly from the use of the materials.

⚠ WARNING

CANCER and REPRODUCTIVE HARM - www.P65Warnings.ca.gov

TYPICAL PHYSICAL DATA

Colors	Gray
Stain and Color Change, ASTM C510	No change
Hardness, Shore A, ASTM C661	22
Tack Free Time, ASTM C679	≤ 35 minutes
Joint Movement, ASTM C719	+/- 35%
Adhesion-in-Peel, ASTM C794	25 pli
Tensile Strength, ASTM D412	130 psi (.90 MPa)
Tensile Elongation, ASTM D412	528%
Tear Strength, ASTM D624	55 pli
Volatile Organic Content, ASTM D2369	12.45 g/l
Gun Grade	Zero slump
Viscosity	1,220,000 cp +/- 300,000 cp, Brookfield RVF TF Spindle, 4 RPM, 73°F (23°C)
Shrinkage	No visible shrinkage after 14 days
Service Temperature	-40°F To 200°F (-40°C to 93°C)
Note: Data obtained at 70°F (21°C). ASTM Standards are current unless otherwise stated.	

VOC Compliance (Volatile Organic Compound)

Meets U.S. EPA 40 CFR 59 Subpart C & D; CARB: California Air Resource Board; LADCO: Lake Michigan Air Directors Consortium (Illinois, Indiana, Michigan, Wisconsin); MRPO: Midwest Regional Planning Organization (Illinois, Indiana, Michigan, Ohio, Wisconsin); SCAQMD: South Coast Air Quality Management District (Los Angeles, Orange, Riverside, San Bernardino Counties); and CEPA/EC: Canada Environmental Protection Agency/Environment.



USGBC and related logo is a trademark owned by the U.S. Green Building Council and is used by permission.