



By CTS Cement Manufacturing Corp.

CSI SECTION 32 01 00 – OPERATION AND MAINTENANCE OF EXTERIOR IMPROVEMENT

Fast-Setting, Cement-Based Pothole Fill & Repair Material

EDITOR NOTE: The following guideline specification has been prepared to assist architects and design professionals in the preparation of project master specifications. It is intended for use by qualified design professionals and is not intended to be used verbatim. Appropriate modifications to meet specific project requirements are required. Make appropriate [selections] where options are provided and delete items that are not applicable to the project. Contact CTS Cement Technical Service for additional information or project specification assistance.

PART 1 - GENERAL

1.1 SECTION INCLUDES

- A. Cleaning of existing Asphalt surface.
- B. Supply and installation of Fast-Setting, Cement-Based Pothole Fill & Repair Material
- C. Scope of Work as indicated on drawings, including:
 - [1. Repair of deteriorated asphalt.
 - [2. Resurfacing of damaged or spalled asphalt surfaces.

1.2 RELATED SECTIONS

- [A. Section 32 01 16 – Flexible Paving Rehabilitation
- [B. Section 32 01 17 – Flexible Paving Repair
- [C. Section 32 12 16 – Asphalt Paving
- [D. Section 32 16 00 – Curb, Gutter, Sidewalks, and Driveways

EDITOR NOTE: Modify References as needed for the project. Include appropriate standards related to concrete reinforcement repair or replacement.

1.3 REFERENCES

- A. ASTM C403 Standard Test Method for Time of Setting of Concrete Mixtures by Penetration Resistance

1.4 SUBMITTALS

- A. General: Submit samples and manufacturer's product data sheets, installation instructions, etc. in accordance with Division 01 General Requirements Submittal Section.
- B. Test Data: Submit qualified testing data that confirms compliance with specified performance requirements.
- C. Project Record Documents: Submit accurate records of locations of structural reinforcement repairs indicating type of repair and material(s) used.

1.5 QUALITY ASSURANCE

- A. Qualifications:
 - 1. Manufacturer:
 - a. Repair and resurfacing materials and complementary admixture or bonding agents



By CTS Cement Manufacturing Corp.

materials must be manufactured by or approved for use by CTS Cement Manufacturing Corp. (800-929-3030, www.CTScement.com) and distributed by the same or an authorized CTS Cement dealer.

1.6 MOCK-UP(S)

- A. Test each type of maintenance procedure required on each type of existing construction to determine the most appropriate procedures to use and as a record of expected results.
- B. Crack Injection: Prepare one (1) sample of each type of injection.
- C. Horizontal Surface Repair: [_____] total square area demonstrating each type of repair.
- D. All mock-ups must be approved by the [Architect,] [Owner,] [Engineer] prior to proceeding with work. Mock-ups and samples must remain on site until project completion and final acceptance.

1.7 DELIVERY, STORAGE, AND HANDLING

- A. Delivery: Deliver products in original, unopened, undamaged packaging with manufacturer's identification (i.e., brand logo, product name, weight of packaged unit, lot number).
- B. Storage: Store products in a dry location, covered, out of direct sunlight, off the ground, and protected from moisture. Maintain storage temperature required by the manufacturer. Keep materials dry until used. Store bulk sand in a well-drained area on a clean, solid surface. Cover sand to prevent contamination. Protect materials from temperature extremes.
- C. Handling: Handle products in accordance with manufacturer's published recommendations.

1.8 SITE / ENVIRONMENTAL CONDITIONS

- A. Temperature: Maintain ambient and surface temperatures between 45°F (7°C) to 90°F (32°C). Do not apply materials if ambient temperature falls below 45°F (7°C) within 24 hours of application. Protect from uneven and excessive evaporation during dry weather, windy conditions and strong blasts of dry air.
- B. Inclement Weather: Do not apply repair or resurfacing materials during inclement weather unless appropriate protection is employed.
- C. Sunlight Exposure: Avoid, whenever possible, installation of repair or resurfacing materials in direct sunlight which could adversely affect aesthetics.
- D. Substrate: Prior to installation, the substrates must be properly cleaned and prepared to receive repair or resurfacing materials, then inspected for proper preparation and any surface contamination or other conditions that may adversely affect the performance of the materials. Substrate must be free of residual moisture.

1.9 COORDINATION AND SCHEDULING

- A. Coordinate installation of materials with all other trades to avoid impeding other construction.
- B. Sufficient manpower must be provided to ensure continuous application and timely finishing.

PART 2 - PRODUCTS

2.1 MANUFACTURERS

- A. Basis of Design: CTS Cement Manufacturing Corp., 12442 Knott Street, Garden Grove, CA 92841 (800-929-3030, www.CTScement.com).
- B. Components: Obtain repair or resurfacing materials, complementary admixtures and bonding



By CTS Cement Manufacturing Corp.

agents manufactured by CTS Cement from authorized distributors. No substitutions or additions of other materials are permitted without prior written permission from the manufacturer for this project.

2.2 MATERIALS

A. Fast-Setting, Cement-Based Pothole Fill & Repair Material – General

1. Rapid Set® ASPHALT REPAIR MIX is a high-performance, fast-setting, multipurpose, cementitious material with coarse aggregate for asphalt repair. ASPHALT REPAIR MIX has been specially formulated with a polymer-modified blend of Rapid Set Cement and additives designed to match the color of typical existing asphalt. Combine ASPHALT REPAIR MIX with water to produce a high-quality repair material that is ideal for pothole repairs. ASPHALT REPAIR MIX has superior adhesion to most substrates. ASPHALT REPAIR MIX has a working time of 15 minutes and achieves drive-on strength in 2 hours.
2. Additives and admixture materials must be approved for use by CTS Cement Manufacturing Corp. prior to use. (800-929-3030, www.CTScement.com)

B. Water: Clean, potable water free of deleterious amounts of silt and dissolved salts.

2.2 MATERIAL PROPERTIES

A. High Performance, Asphalt Colored, Cement-Based Repair Material– General

1. Rapid Set® Resurfacer:
 - a. Minimum performance requirements:

Set Time (ASTM C403)	Initial Set Final Set	90 minutes 120 minutes
---------------------------------	--------------------------	---------------------------

2.3 RELATED MATERIALS

- A. Admixtures: Do not add additional dry materials such as cement, sand, additives or admixtures. Mix only with water. All additives and admixture materials must be approved for use by CTS Cement Manufacturing Corp. prior to use. (800-929-3030, www.CTScement.com)

PART 3 - EXECUTION

3.1 EXAMINATION

- A. Verify project site conditions under provisions of Section 01 00 00.
- B. Compliance: Comply with manufacturer's instructions for installation of repair and resurfacing materials.
- C. Coordinate installation with adjacent work to ensure proper sequencing of construction.
- D. Protect adjacent and surrounding surfaces not specified to receive materials with necessary means to ensure protection against overspray, water or other harmful debris.
- E. Advise Contractor of discrepancies preventing proper installation of materials. Do not proceed with the work until unsatisfactory conditions are corrected.

CLEANING

- F. Protect surrounding area by providing enclosures, barricades and other temporary construction as required to protect adjacent work from damage.
- G. Clean asphalt surfaces, cracks and voids of dirt or other contamination using the most appropriate



By CTS Cement Manufacturing Corp.

method for proper preparation. Ensure methods are in compliance with material manufacturer's recommendations.

- H. Do not use any of the following cleaning methods unless approved by the [Architect,] [Engineer,] and the repair and resurfacing materials manufacturer:
 - 1. Brushes with wire bristles, grinding with abrasives, solvents, hydrochloric or muriatic acid, sodium hydroxide, caustic soda, or lye.
 - 2. Soap or detergent that is not non-ionic.
 - 3. Water washing pressure over 100 psi.
 - 4. Steam-cleaning or steam-generated hot-water washing.
 - 5. Alkaline cleaning agents.
 - 6. Acidic cleaning agents.
 - 7. Abrasive blasting.

3.2 PREPARATION

- A. Comply with manufacturer's printed instructions.

3.3 MIXING

- A. Organize installation personnel and equipment before mixing begins.
- B. Comply with manufacturer's printed instructions.
- C. Adjust water to achieve the desired consistency. Do not exceed manufacturer's recommendations.
- D. All additives and admixture materials must be approved for use by CTS Cement Manufacturing Corp. prior to use. (800-929-3030, www.CTScement.com)
- E. Do not re-temper, add water, or remix after material stiffens. Material that stiffens before use must be discarded.

3.4 APPLICATION

- A. Have all required tools, equipment and materials organized and as close to the placement area as possible.
- B. Comply with manufacturer's printed instructions.
- C. Build up the materials to completely cover/fill the repair area flush with the existing surface.
- D. On flat work, do not install layers. Install full-depth sections and progress horizontally.
- E. Limit the amount of vibration during placement to prevent segregation.

3.5 CURING

- A. Comply with manufacturer's printed instructions for appropriate curing methods.

3.6 CLEAN-UP

- A. Remove and legally dispose of concrete repair and resurfacing debris material from job site.
- B. Clean excess material from surrounding areas and all tools immediately, before material cures. If materials have cured, remove using mechanical methods that will not damage the substrate.
- C. Clean adjacent surfaces as needed using materials and methods recommended by the manufacturer of the material being cleaned. Remove and replace work that cannot be cleaned to the satisfaction of the Project Designer/Owner.



By CTS Cement Manufacturing Corp.

END OF SECTION

Rev. February 2020

This sample guideline specification is intended for use by a qualified design professional. The sample guideline specification is not intended to be used verbatim as an actual specification without appropriate modifications for the specific project requirements.